

 山东博汇纸业股份有限公司 SHANDONG BOHUI PAPER INDUSTRIAL CO.,LTD.								生效日期 Effective Date		20230309		
								版本 Version		4.0		
高白胶版印刷纸OHB8 High White Offset Paper												
检测项目 Items	单位 Unit	检验方法 Test Method	标准 Standard									
			60	65	70	75	80	90	95	100	115	120
定量 Grammage	g/m²	GB/T451.2 ISO536	60 ±2	65 ±2	70 ±2	75 ±2	80 ±2	90 ±2	95 ±2	100 ±3	115 ±3	120 ±3
厚度 Thickness	µm	GB/T451.3 ISO534	76 ±4	81 ±4	88 ±4	94 ±4	100 ±4	108 ±4	115 ±4	120 ±4	135 ±4	142 ±4
Cobb-Top/Back (60s)	g/m²	GB/T1540 ISO535	20.0-45.0									
亮度-Top/Back Brightness (D65)	%	GB/T7974 ISO2470	100.0±3.0									
视白度 CIE Whiteness	%	GB/T22880 ISO11475	148.0±3.0									
不透明度 Opacity	%	GB/T1543 ISO2471	≥86.0		≥90.0					≥93.0		
BEKK 平滑度 Smoothness	s	GB/T456 ISO5627	Top: ≥40.0 Back: ≥35.0									
水分 Moisture	%	GB/T462 ISO287	5.5±1.0									
耐折度 CD Folding	Times	GB/T457 ISO5626	≥6									
印刷表面强度 IGT-Picking	m/s	GB/T2236 5 ISO3783	≥1.8									
抗张指数 MD Tensile index	N.m/g	GB/T1291 4 ISO1924	≥55.0									
检测条件 Testing Condition: 温度 Temperature: (23±1)℃ 相对湿度 Relative Humidity: (50±2)%RH												
产品特点 Product Characteristics:												
1、精选优质木浆，全木浆抄造。 All wood pulp paper, which selected high-quality wood pulp .												
2、匀度好，厚度好，挺度佳。 Good formation,high thickness and stiffness.												
3、机械强度高，尺寸稳定性好，多色套印准确；表面强度好，不易掉粉掉毛，适合高速轮转胶印、单张纸胶印。 High strength, good dimensional stability and accurate multi-color overprint; suitable for high-speed rotary offset (4colors) and sheet fed offset printing.												
5、高亮度，色泽亮丽，网点再现性佳，适合精制书刊、杂志等要求。 High brightness, bright color, good dot reproducibility, suitable for refined books, magazines and other requirements.												